



Flame Retardant fabric for FR-clothing

# Etna

99% COTTON / 1% AS

350 GSM / SATIN 4/1



Fabric name	Etna
Fabric weight	350 g/m <sup>2</sup> ± 5%
Composition	99% Cotton, 1% Antistatic
Full width	152 cm
Weave	Satin 4/1
Finishes	Flame Retardant
Application	FR workwear jackets, trousers and coveralls
Washing instruction	

## FR & SPECIAL PROPERTIES

Flame retardant	EN ISO 11612:2015 A1 & A2, B1, C1, E3, F1	EN ISO 11611:2015 Class 1
Anti static	EN 1149-5 (1149-3 method 2)	
Electric arc	EN 61482-1-2 Class 1 (4kA)	IEC 61482-1-1 ATPV 16 cal/cm <sup>2</sup> , HAF 83%

## PHYSICAL PROPERTIES

		warp	weft
Tensile strength, N	ISO 13934-1:1999	1200 N	700 N
Tearing strength, N	ISO 13937-2:2000	30 N	55 N
Dimensional Stability To Washing, max	ISO 5077-ISO 15797	3%	
Abrasion Resistance	ISO 12947-2:1999	21,000 rubs	
Pilling Resistance	ISO 12945-2:2001	4	

## COLOUR FASTNESS

			Light	Mid	Dark	Special colors
			Orange, Yellow, Red	Green, Grey, Royal Blue	Dark Navy, Navy, Royal Blue	Black
Wash Fastness Method E2S (95°C)	ISO 105-C06	Colour Change	4-5	4-5	4-5	4-5
		Stain on Polyester	4-5	4-5	4	4
		Stain on Cotton	4	4	4	3-4
Rub Fastness	ISO 105-X12:1995	Wet	3	3	2-3	2
		Dry	4	4	4	4
Light Fastness	ISO 105-B02		3	4	4	4

### XM Textiles Europe

Email: [info@xmtextiles.com](mailto:info@xmtextiles.com)  
www.xmtextiles.com

Darius ir Gireno st. 42A Office 509  
Vilnius LT – 02189 Lithuania  
Tel: +370 (347) 20299

Sos.Tamasi 20, Hala 3A, et. 1  
Buftea (platforma Rombiz), Romania  
Zip 070000, Tel: +40 31 630 36 39