



Flame Retardant fabric for FR-clothing

Sonora-185AS

80% COTTON / 19% POLYESTER / 1% AS

185 GSM / PLAIN 1/1



Fabric name	Sonora-185 AS
Fabric weight	185 g/m ² ± 5%
Composition	80% Cotton, 19% Polyester, 1% AS
Full width	152 cm
Weave	Plain 1/1
Finishes	Flame Retardant
Application	Workwear light jackets, trousers and coveralls
Washing instruction	

FR & SPECIAL PROPERTIES

Flame retardant	EN ISO 11612 A1, A2, B1,C1
Antistatic	EN 1149-5 (1149-3 method 2)

PHYSICAL PROPERTIES

		warp	weft
Tensile strength, N	ISO 13934-1:1999	750 N	430 N
Tearing strength, N	ISO 13937-2:2000	19 N	18 N
Dimensional Stability To Washing, max	ISO 5077-ISO 15797	3%	
Abrasion Resistance	ISO 12947-2:1999	17,000 rubs	
Pilling Resistance	ISO 12945-2:2001	4	

COLOUR FASTNESS

			Light	Mid	Dark	Special colors
			Orange, Yellow	Green, Grey, Royal Box	Dark Navy, Navy, Royal Blue	Black
Wash Fastness Method E2S (95°C)	ISO 105-C06	Colour Change	4-5	4-5	4-5	4-5
		Stain on Polyester	4	4-5	4	4
		Stain on Cotton	4-5	4-5	4-5	4
Rub Fastness	ISO 105-X12:1995	Wet	4	3	3	3
		Dry	4-5	4	4	4
Light Fastness	ISO 105-B02		3	4	4	4

XM Textiles Europe

Email: info@xmtextiles.com
www.xmtextiles.com

Darius ir Gireno st. 42A Office 509
Vilnius LT – 02189 Lithuania
Tel: +370 (347) 20299

Sos.Tamasi 20, Hala 3A, et. 1
Buftea (platforma Rombiz), Romania
Zip 070000, Tel: +40 31 630 36 39